РЕКОНСТРУКЦИЯ НА ГРЪДНАТА СТЕНА С ХЕТЕРОЛОЖЕН АЦЕЛУЛАРЕН ДЕРМАЛЕН МАТРИКС - КЛИНИЧЕН СЛУЧАЙ

Й. Йорданов¹, А. Шеф², Х. М. Ласо³

¹Отделение по пластична хирургия и изгаряния,
Военномедицинска академия-София,

²Катедра по дерматовенерология и алергология,
Военномедицинска академия-София

³Отделение по пластично-възстановителна и
естетична хирургия, Университетска болница
Грегорио Мараньон-Мадрид, Испания

АБСТРАКТ

Реконструкцията на гръдната стена е предизвикателство, особено след настъпили инфекциозни усложнения като медиастинит. Локализацията и големината на дефекта играят важна роля при избора на метода на реконструкция, като постигането на добър естетичен и функционален краен резултат е основна цел. За стабилизиране на гръдната кост се прилагат различни алопластични материали, а локо-регионалните ламба осигуряват надеждно мекотъканно покритие с добре кръвоснабдена тъкан. Въпреки многобройните продукти, които днес са на разположение, ацелуларните дермални матрикси имат определени предимства, които биха били от полза при реконструкцията на предния медиастинум и гръдната стена. В настоящата статия авторите представят случай на пациент с медиастинит след сърдечно-съдова операция и последвал неуспех на реконструктивната интервенция. След проведено консервативно лечение и терапия с негативно налягане, са използвани титанови плаки за възстановяване интегритета на гръдната кост. Ацелуларен дермален матрикс от свински произход е приложен за подсилване и консолидиране на фиксиращите плаки и мекотъканната реконструкцията, извършена с локални мускулни ламба. Благодарение на способността си да се инкорпорира и реваскуларизира, да проявява устойчивост на раневи инфекции и да дава допълнителна стабилност, ацелуларният дермален матрикс изглежда обещаваща, макар и навярно не достатъчно ефективна алтернатива на синтетичните материали при реконструкцията на стернума и предната гръдна стена.

ANTERIOR CHEST WALL RECONSTRUCTION WITH HETERO- LOGOUS ACELLULAR DERMAL MATRIX- CLINICAL CASE REPORT

Y. Yordanov¹, A. Shef², J. M. Lasso³

¹Unit of Plastic Surgery and Burns- Military
Medical Academy, Sofia,

²Department of Dermatovenereology and
Allergology, Military Medical Academy, Sofia,

³Unit of Plastic Reconstructive and Aesthetic
Surgery- University Hospital Gregorio Marañón,
Madrid, Spain

ABSTRACT

Anterior chest wall reconstruction is a challenging initiative, particularly after deep sternal infection. The location and the size of the defect play a major role when selecting the method of repair, while good aesthetic and functional outcome remain a primary goal. Alloplastic materials are often used for sternal stabilization and loco-regional flaps are applied to provide well vascularized soft tissue coverage. Although numerous products are available today, acellular dermal matrices have some advantage that could be of benefit in the repair of the anterior mediastinum and chest wall. In this clinical report, we present a case of a patient with poststernotomy mediastinitis and wound dehiscence after cardiovascular surgery and failure of the initial chest wall repair. After conservative treatment and Negative Pressure Wound Therapy, titanium plates were used to restore the sternal continuity. Acellular dermal matrix of porcine origin was applied for improving and reinforcing the fixation plates and soft tissue repair accomplished by local muscle flaps. Due to its ability to become incorporated and vascularized, to resist wound infections and to provide stability, acellular dermal matrix seems to be a promising although probably not enough efficient alternative of the synthetic materials in sternal reconstruction and anterior chest wall repair.

Key words: porcine acellular dermal matrix, Strattice, anterior chest wall, mediastinitis, sternal reconstruction.

INTRODUCTION

Mediastinitis with sternal dehiscence is one of the most dreaded complications after median sternotomy, resulting in significant morbidity and

Ключови думи: свински ацелуларен дермален матрикс, Stratrice, предна гръдна стена, медиастинит, реконструкция на стернума.

УВОД

Медиастинитът с дехисценция на гръдната кост е едно от най-опасните усложнения след срединна стернотомия с висок морбидитет и смъртност. Честотата на медиастинита след конвенционална сърдечна операция варира в диапазона от 0.3 % до 5% (1). Болнична смъртност при това усложнение е от 8% до 25 %, като също така води до рязко увеличение на продължителността на болничния престой и разходите за лечение (2). Реконструкцията на медиастинума е предизвикателство и често налага мултидисциплинарен подход с участието на пластичен хирург.

Схващанията по отношение на лечението на медиастинита и стерналната дехисценция еволюират значително през последните години. Особен напредък се отбелязва в оперативните техники и следоперативните грижи. През 1963 г. Shumacker и Mandelbaum (3) разработват първия метод за лечение на медиастинит, включващ хирургичен дебридман (ексцизионно почистване), последван от директно затваряне над иригационни катетри. Въпреки първоначалния ентузиазъм, този метод дава незадоволителни резултати по отношение на патологичната поразеност и смъртността, което се оказва важна предпоставка за въвеждането на мускулните ламба в реконструкцията на стернума през 1980 (4). По-късно вакуум-асистираната терапия (т. нар. VAC-терапия) започва да се използват в лечението на стерналните дефекти и позволяват постигането на добри резултати в дългосрочен план (5,6). В последните години биват въведени нови устройства за възстановяване на стернални дефекти, които намират приложение при определени случаи (7).

Резекцията на гръдната кост и мускуло-кутанните ламба са добър подход при високо-рискови пациенти. Той осигурява ефективен контрол на инфекцията и приемливи резултати по отношение на контрола на болката и качеството на живот (8). Мекотъканните ламба, като мускулните и оментума, осигуряват добре кръвоснабдена мека тъкан за покритие, когато за стабилизация на гръдната кост се използват различни алопластични материали. Мекотъканно ламбо на първи избор е големият пекторален мускул, поради лесния достъп и по-ниския морбидитет

mortality. The reported incidence of mediastinitis after open heart surgery ranges from 0.3% to 5% in the literature (1). It carries an in-hospital mortality rate of 8% to 25% and leads to a dramatic increase in length of hospital stay and overall health care costs (2). Mediastinal reconstructions could be challenging and often require a multidisciplinary approach including a plastic surgeon.

The treatment of sternal dehiscence and mediastinitis has evolved over the years with major improvements in postoperative care and advancements of operative techniques. In 1963, Shumacker and Mandelbaum (3) devised the first method of treating mediastinitis involving surgical debridement followed by primary closure over irrigation catheters. However, this method yielded unsatisfactory results with high morbidity and mortality rates, leading to the use of muscle flaps for sternal reconstruction in the 1980 (4). More recently, vacuum-assisted closure (VAC) dressings have been used in the management of sternal wound and have allowed good long-term results to be achieved (5,6). Lastly, novel sternal closure devices have also been used in the management of selected cases (7).

Sternal resection and musculocutaneous flaps are a good approach for high-risk patients. It provides an effective control of the infection and acceptable results in terms of pain control and quality of life (8). Soft tissue flaps like muscle flaps and omental flaps are generally needed to provide well vascularized tissue when alloplastic materials are used for sternal stabilization being the pectoralis major flap the first-choice procedure because of its easy access and less morbidity (9).

Despite all the improvements, there is no singular strategy for the management of mediastinitis with sternal dehiscence after open heart surgery. Although there are numerous studies reported in the literature, to date there is not a consensus regarding the method of sternal wounds debridement and the technique for definitive closure.

The use of porcine acellular dermal matrix (ADM) has been well described and significantly increases during the last decade in the field of reconstructive surgery (10-12). It is recommended for use in soft-tissue repair because of its resistance to infection, lack of adhesion formation and the advantage of becoming vascularized and incorporated autologously. Considering all these facts Stratrice™ Tissue Matrix seems to be a promising alternative to synthetic materials in some circumstances. Nowadays it is basically applied in the breast surgery and for abdominal wall repair (Table 1) (13,14).

на донорното място (9).

Въпреки всичките подобрения и напредъка в науката и практиката, няма универсално приета стратегия за лечението на медиастинита и стерналната дехисценция след открита сърдечна операция. Въпреки множеството проучвания, към днешна дата не съществува консенсус и по отношение на точния метод за дебридиране и техниката за окончателно затваряне на стерналния дефект.

Употребата на свинския ацелуларен дермален матрикс (АДМ) в областта на реконструктивна хирургия значително нараства през последното десетилетие и е добре описана (10-12). Той се употребават при реконструкция на меките тъкани, поради своята устойчивост към инфекции, липсата на груби сраствания и предимството да се реваскуларизира и интегрира в собствените тъкани на организма. Имайки предвид всички тези факти, АДМ от свински произход Strattice™ изглежда обещаваща алтернатива на синтетичните материали при определени обстоятелства. Днес този биологичен продукт се прилага основно при операции на женската гърда и при реконструкция на коремната стена (Табл. 1) (13,14).

В настоящата статия представяме клиничен случай, при който успешно сме приложили свински АДМ като основен компонент на комплексна реконструкция на стернума след медиастинит.

КЛИНИЧЕН СЛУЧАЙ

Представяме случай на 72-годишен мъж с хронична исхемична болест на сърцето, на когото е направен троен аорто-коронарен байпас. На осмия следоперативен ден пациентът развива сърдечна тампонада и втора такава 38 часа след първата. Така, в рамките на 48 часа, на пациентът биват извършени две стернотомии респективно. Като постоперативни усложнения пациентът развива бъбречната недостатъчност и пневмония с респираторен дистрес, причинена от *Serratia marcescens*. След последната стернотомия екипът кардиохирурзи извършва реконструкция чрез серкляж на стернума със стоманена сутура и мекотъканно покритие с двустранни ламба от големите пекторални мускули. В постоперативния период настъпва стернална дехисценция и микробиологичното изследване доказва локален инфекциозен процес, причинен от *Staphylococcus epidermidis*. Шест седмици по-късно е поискана консултация с пластичен хирург, на което се отзовава нашият екип.

We report a clinical case where a porcine ADM has been successfully applied as a main component of a complex sternal reconstruction.

Case report

A 72-year-old man diagnosed of chronic ischemia cardiopathology underwent triple-vessel coronary artery bypass grafting. On the eighth postoperative day he developed a cardiac tamponade and another one 38 hours later. Two sternotomies were applied in 48 hours respectively. These events were associated to renal failure and pneumonia by *Serratia marcescens* with respiratory distress. A sternal fixation with steel cerclage wires and bilateral pectoralis major flaps were performed by cardiac surgeons after the last sternotomy. This procedure resulted unable to solve the chart and dehiscence occurred. Microbiological study demonstrated *Staphylococcus epidermidis* infection. Six weeks later the plastic surgeons of our team were called to evaluate the patient for possible reconstruction.

We found a wound with purulent secretion and necrotic tissue; a divided sternum in the midline with bony instability was presented. We established a treatment comprising aggressive necrotic tissue debridements, VAC-therapy and intravenous antibiotherapy for four weeks. When three consecutive cultures of the sternal wound resulted negative, a reconstructive approach was considered to perform a sternal fixation, wound closure and soft tissue coverage.

First, a titanium plate was applied to make the osteosynthesis and then a Strattice patch was placed above (Fig. 1). Then we used the pectoralis muscle flaps to overlap and protect the ADM. After ten days, another sternal dehiscence was presented, but the wound cultures were negative. We established an irrigation treatment with saline serum for 3 weeks and a new osteosynthesis was performed. We observed that there was a granulation tissue growing in the lateral aspects of the ADM, and fibrous tissue was presented between the medial borders of the sternal bone giving it bony stability at certain degree. Biopsies by punch were taken for histological study in order to verify the ADM integration (Fig. 2). For the reconstruction aim at that time a new titanium plate was applied with a patch of Strattice wrapped around it (Fig. 3). The remaining parts of the pectoralis major flaps were placed above. Then a second ADM was sutured over the union of both flaps in order to reinforce the soft tissue coverage. No complications were registered in the postoperative period and after 23 days of follow-up the patient was discharged from the hospital (Fig. 4).

Таблица 1. Сравнителна характеристика на основните видове АДМ, използвани в сферата на реконструктивната хирургия. Таблицата е приложена в оригиналния си вид с оглед избягване на евентуално двусмислие при превода на определени термини (13).

Biologic	Source	Processing	Sterile	Indications	Components	Advantages	Other
AlloDerm	Cadaveric human skin	Processed to remove cells and antigenic components	No	Breast, pelvic, and head and neck reconstruction; abdominal hernia repair	Collagen, hyaluronic acid, elastin, fibronectin, proteoglycans, vascular channels	Tolerates irradiation One of original ADMs; well documented in literature	Non-cross-linked; requires rehydration time
Strattice	Porcine ADM	Proprietary process that removes cells with antigenic response	Yes	Breast reconstruction, abdominal wall repair	Undisclosed	Permits white cell migration, cell repopulation and revascularization Excellent biomechanical strength Can be used in local treatment in the presence of infection Minimizes adhesions to implant	Non-cross-linked
DermaMatrix	Human skin	Sodium chloride used to remove epidermis and dermis	Yes	Nasal, lower eyelid, and breast reconstruction; cleft palate repair, abdominal wall repair	Collagen, elastin	Rapid rehydration Bacterial inactivation Does not need to be refrigerated for storage	Non-cross-linked
SurgiMend	Fetal bovine dermal collagen	Process designed to remove cellular components and potentially infectious agents from raw material	Yes	Muscle flap reinforcement; hernia repair, including abdominal, inguinal, diaphragmatic, femoral, scrotal, umbilical, and incisional hernia repair	Type I and type III collagen	Easy to handle and suture, rehydrates in minutes Unique shapes and sizes Fenestrated to assist in fluid drainage	Non-cross-linked
Veritas	Bovine pericardium	Proprietary process that caps free amine groups	Yes	Abdominal hernia repair	Collagen	Excellent strength and suture retention Similar to autologous tissue Reduces tissue attachment Remodels for rapid integration into surrounding tissues	Non-cross-linked
FlexHD	Human allograft skin		No	Abdominal hernia repair, breast reconstruction, chest wall reconstruction	Collagen	Prehydrated Low operative costs Minimal elasticity	Non-cross-linked

При физикалното изследване установихме налична рана в стерналната област с пурулентен ексудат и некротични тъкани; налична дехисценция на стернума по срединната линия с костна нестабилност. Започна се лечение, включващо агресивен хирургичен дебридман (ексцизионно почистване на некротичните тъкани) и VAC-терапия под интравенозно антибиотично покритие в продължение на четири седмици. След като три последователни микробиологични култури бяха отрицателни, се

DISCUSSION

At the time of anterior chest wall reconstruction in patients with poststernotomy mediastinitis (also commonly called deep sternal wound infection), a preservation of the sternum should be the principal aim of surgical treatment. From the other hand, aggressive surgical treatment by debridement is crucial for the success of the healing process. Chest wall reconstruction following extensive resection is greatly facilitated by the use of vascularised flaps and plastic surgeons are often asked to assist with

премина към същинската реконструктивна част от лечението, целяща фиксиране на стернума, затваряне на раната и осигуряване на добро мекотъканно покритие.

При приложената оперативна техника първо извършихме стернална остеосинтеза с титаниеви плаки и поставихме отгоре парче свински АДМ-Strattice (Фиг. 1). След това използвахме големите пекторални мускули за покриване и предпзване на АДМ. Десет дни по-късно отново настъпи стернална дехисценция, но микробиологичните посевки не пораждаха бактериален растеж. Като терапевтична мярка бяха приложени ежедневни промивки с физиологичен серум в продължение на 3 седмици, след което бе направена нова остеосинтеза. По време на интервенцията установихме наличие на грануляционна тъкан в периферните части на поставения преди това АДМ, като също така между медиалните ръбове на разединената гръдната кост бе налична начална фиброзна тъкан, обуславяща известна костна стабилност. Бяха взети пънч-биопсии за хистологично изследване с цел да се провери тъканната интеграция на АДМ (Фиг. 2). За реконструкцията използвахме нова титаниева плака, обвита в ново парче Strattice (Фиг. 3). Остатъчните части от пекторалните ламба бяха защити върху така извършената реконструкция, след което върху тях монтирахме втори АДМ с цел подсилване на мекотъканното покритие. Постоперативният период премина без усложнения и пациентът бе изписан на 23-и следоперативен ден (Фиг. 4).

ДИСКУСИЯ

Запазването на гръдната кост следва да бъде основна цел при реконструкцията на гръдната стена при пациенти с постоперативен медиастинит, често наричан в англоезичната литература deep sternal wound infection. От друга страна, агресивният хирургичен дебридман е от решаващо значение за успеха на оздравителния процес. Прилагането на васкуляризиран ламба от своя страна значително улеснява реконструкцията на гръдната клетка след обширни резекции, поради което пластичните хирурзи често са част мултидисциплинарния екип, анагажиран с лечението на тази група пациенти. От особена важност за реконструкцията е постигането на костна стабилност.

Конвенционалните подходи за лечение на постоперативния медиастинит обикновено включват ревизия с отворени превръзки

coverage of large chest wall defects. However, in addition to soft tissue coverage, we need to address the requirement for skeletal support.

Conventional forms of treatment usually involve surgical revision with open dressings or closed irrigation and reconstruction with vascularized soft tissue flaps such as omentum, pectoralis muscle or even rectus abdominis flaps (9). Vacuum-assisted closure therapy acts as a link between radical debridement and definitive plastic coverage (6).

Since the sternal instability is a serious complication after median sternotomy, an important complement to the traditional reconstructive procedures in mediastinal reconstruction are the alloplastic materials. Biomechanical studies have suggested superiority of rigid plate fixation over wire cerclage for sternal fixation (15). Other type of alloplastic materials can provide stability of the chest wall, but unfortunately there are not many publications about its use in mediastinal reconstruction (16).

Chest wall reconstruction was carried out also by using a human ADM. The authors concluded that human acellular dermis is an effective but expensive alternative to synthetic mesh in reconstruction of chest wall and diaphragmatic defects including under conditions of potential or overt contamination (17). In 2011 Huston et al (18) reported a case of chest wall reconstruction with porcine ADM (Strattice) and a latissimus dorsi myocutaneous flap. Strattice™ tissue reconstructive matrix (LifeCell, Branchburg, NJ, USA) is a porcine ADM widely applied in the plastic surgery procedures: expander/implant breast reconstruction and aesthetics (13,14), abdominal wall repair (11), burn surgery (19), among others. The biopsy of the Strattice demonstrated mild fibroblastic reaction with focal tissue integration of the matrix (20,21). Capillaries ingrowth in the matrix was clearly evident (21).

In our patient, the porcine ADM was perfectly incorporated into the sternal bone and the anterior aspects of the chest wall. The presence of granulation tissue around the external limits of the patch was a sign of good integration of the ADM into the anterior chest wall. Interestingly, it had been promoted a sufficient healing of the sternal bone despite the dehiscence after the first operation performed by our team. On the other hand, cultures were negative after the operation and that logically contributed to good stability of the sternum. For that reason during the second reconstructive procedure we used only one plate in order to reinforce the sternum; the rests of pectoralis major muscles were applied just for soft tissue coverage.

Figure 1: Porcine acellular dermal matrix (Strattice) placed on the osteosynthesis of the sternal bone performed with titanium plates.

Figure 2: HE staining: a fibroblastic reaction with focal tissue integration of the matrix.

Figure 3: Sternal osteosynthesis with a titanium plate fitted over a patch of Strattice matrix.

Figure 4: (A) Sternal wound with purulent discharge, necrotic tissue and bony instability at the time of the initial consultation by our team. (B) Final outcome, 6 months after the final reconstructive procedure.

или затворени промивки и реконструкция с васкуляризиран мекотъкан ламба, като например оментум, голям пекторален мускул или дори прав кореман мускул (9). Реконструкцията с помощта на VAC-терапия се явява междинно звено между радикалния дебридман и дефинитивното пластично възстановяване (затваряне на дефекта) (6).

Тъй като стерналната нестабилност е сериозно усложнение след срединна стернотомия, важен елемент в реконструкцията на медиастинума са алопластичните материали. Биомеханичните проучвания показват превъзходство на фиксацията с плаки пред серкляжа на гръдната кост (15). Освен споменатите, и други видове алопластични материали биха могли да осигурят стабилност на гръдната клетка, но все още липсват достатъчно публикации по отношение на тяхната употреба (16).

При реконструкцията на гръдната стена се използва също и човешки АДМ. Авторите на едно от обстойните проучвания по темата стигат до заключението, че човешкият АДМ е ефективна, но скъпа алтернатива на синтетичните мрежи при реконструкцията на дефекти на гръдната стена и диафрагмата, ефективна включително в условията на контаминация (17).

През 2011 г. Huston и съавтори (18) докладват случай на реконструкция на гръдната стена със свински АДМ (Strattice) и миокутанно ламбо от m.latissimus dorsi. Реконструктивният матрикс Strattice™ (LifeCell, Branchburg, NJ, USA) е свински АДМ, който е широко прилаган в пластичната хирургия: при естетичната и реконструктивната хирургия на млечната жлеза (чрез импланти и експандери) (13,14), при реконструкцията на коремната стена (11), при изгаряния (19) и др. Биопсихните изследвания на Strattice показват минимална фибробластна реакция с фокална тъканната интеграция (20,21). Капилярното прорастване (реваскуларизация) в матрикса също е добре демонстриран феномен (21).

При нашия пациент, свинският АДМ се намери перфектно инкорпориран в гръдната кост и предната гръдна стена, като наличието на грануляционна тъкан около периферията на парчето бе знак за добрата му тъканна интеграция. Интересното за нас бе, че АДМ бе способствал за заздравяването на гръдната кост, въпреки настъпилата дехисценция след предходната оперативна интервенция. От друга страна, микробиологичните култури бяха отрицателни

CONCLUSION

Application of porcine ADM seems to be an effective method for sternal reconstruction after mediastinitis and sternal dehiscence but further investigations are needed. In Bulgaria, the application of acellular dermal matrices is still a rare occurrence basically because of the high price and inadequate reimbursement of these biological products.

Address for correspondence:

Yordan P. Yordanov, MD, PhD
Military Medical Academy- Sofia, Bulgaria
12th floor, Unit of Plastic Surgery and Burns
3 Georgy Sofiisky Blvd
1606 - Sofia
Tel.: +359 887 56 00 54
e-mail: yordanov_vma@abv.bg

REFERENCES

1. Oakley RM, Wright JE. Postoperative mediastinitis: Classification and Management. *Ann Thorac Surg* 1996; 61: 1030-6.
2. Sjögren J, Malmjö M, Gustafsson R, et al. Poststernotomy mediastinitis: a review of conventional surgical treatments, vacuum-assisted closure therapy and presentation of the Lund University Hospital mediastinitis algorithm. *Eur J Cardiothorac Surg* 2006; 30(6): 898-905.
3. Shumacker HB Jr, Mandelbaum I. Continuous antibiotic irrigation in the treatment of infection. *Arch Surg* 1963; 86: 384-7.
4. Jurkiewicz MJ, Bostwick J 3rd, Hester TR et al. Infected median sternotomy wound: Successful treatment with muscle flaps. *Ann. Surg* 1980; 191(6): 738-44.
5. Obdeijn MC, de Lange MY, Lichtendahl DH, et al. Vacuum-assisted closure in the treatment of poststernotomy mediastinitis. *Ann Thorac Surg* 1999; 68: 2358-60.
6. Agarwal JP, Ogilvie M, Wu LC, et al. Vacuum-assisted closure for sternal wounds: a first-line therapeutic management approach. *Plast Reconstr Surg* 2005; 116(4): 1035-40; discussion 1041-3.
7. Ceresa F, Casablanca G, Patane` F. Complicated sternal dehiscence treated with the Strasbourg thoracic osteosyntheses system (STRATOS) and the transposition of greater omentum: a case report. *J Cardiothorac Surg* 2010; 5: 53.
8. Immer FF, Durrer M, Mühlemann KS, et al. Deep sternal wound infection after cardiac surgery: modality of treatment and outcome. *Ann Thorac Surg* 2005; 80(3): 957-61.
9. Greig AV, Geh JL, Khanduja V, et al. Choice of flap for the management of deep sternal wound infection- an anatomical classification. *J Plast Reconstr Aesthet Surg* 2007; 60(4): 372-8.
10. Tang LL, Liu H, Wang YL, et al. Evaluation of the bio-

след операцията, като липсата на контаминация логично би допринесла за добрата стабилност на гръдната кост. Поради наличната костна стабилност, по време на втората реконструктивна интервенция използвахме само една титаниева плака за стабилизиране на гръдната кост. Остатъците от пекторалните ламба използвахме единствено като мекотъканно покритие.

ЗАКЛЮЧЕНИЕ

Използването на свински АДМ се очертава като ефективен метод за реконструкция на гръдната кост след медиастинит и стернална дехисценция, но по-нататъшни изследвания са необходими, за да бъде потвърдено това. В България прилагането на АДМ все още е рядко явление, основно поради високата цена на тези биологични продукти и неадекватното им реимбурсиране.

Адрес за кореспонденция:

Д-р Йордан П. Йорданов, дм
Военномедицинска академия- София
12-ти етаж, Отделение по пластична хирургия и изгаряния
Бул. „Георги Софийски“ № 3; 1606 София
GSM: 0887 56 00 54
e-mail: yordanov_vma@abv.bg

- compatibility of acellular porcine dermis. *Colloids Surf B Biointerfaces* 2007; 57(2): 215-8. Epub 2007 Feb 11.
11. Gentile P, Colicchia GM, Nicoli F, et al. Complex Abdominal Wall Repair Using a Porcine Dermal Matrix. *Surg Innov* 2011 Oct 16. doi: 10.1177/1553350611421022.
 12. Ellis CV, Kulber DA. Acellular dermal matrices in hand reconstruction. *Plast Reconstr Surg* 2012; 130(5 Suppl 2): 256S-69S doi:10.1097/PRS.0b013e318265a5cf.
 13. Ibrahim AM, Ayeni OA, Hughes KB, et al. Acellular dermal matrices in breast surgery: a comprehensive review. *Ann Plast Surg* 2013; 70(6): 732-8. doi: 10.1097/SAP.0b013e31824b3d30.
 14. Maxwell GP, Gabriel A. Revisionary breast surgery with acellular dermal matrices. *Aesthet Surg J* 2011;31: 700–10.
 15. Song DH, Lohman RF, Renucci JD, et al. Primary sternal plating in high-risk patients prevents mediastinitis. *Eur J Cardiothorac Surg* 2003; 23(6): 943-9.
 16. Weigmann B, Zardo P, Dickgreber N, et al. Biological materials in chest wall reconstruction: initial experience with the Peri-Guard Repair Patch. *Eur J Cardiothorac Surg* 2010; 37(3): 602-5.
 17. Ge PS, Imai TA, Aboulian A, et al. The use of human acellular dermal matrix for chest wall reconstruction. *Ann Thorac Surg* 2010; 90(6): 1799-804.
 18. Huston TL, Taback B, Rohde CH. Chest wall reconstruction with acellular dermal matrix (strattice) and a latissimus myocutaneous flap. *Am Surg* 2011; 77(6): e115-6.
 19. Chen X, Feng X, Xie J, et al. Application of acellular dermal xenografts in full-thickness skin burns. *Exp Ther Med* 2013; 6(1): 194-8. Epub 2013 May 15.
 20. Yordanov Y, Shef A, Vaseva V, Lasso JM. Sternal wound reconstruction with porcine acellular dermal matrix (Strattice) for poststernotomy mediastinitis. *Acta Medica Bulgarica* 2013, vol. XL, № 2: 10-7.
 21. Katerinaki E, Zanetto U, Sterne GD. Histological appearance of strattice tissue matrix used in breast reconstruction. *J Plast Reconstr Aesthet Surg* 2010; 63(12): e840-1.